

# 济南泓海特种玻璃有限公司

## Jinnan Honhai Glass Co., Ltd

### 玻璃管理化性能及主要化学组成

#### Lead free glass tube property and composition

No.			Lead free glass tube (Composition)	Tolerance
1	Density	g/cm <sup>3</sup>	2.62	+/-0.01
2	Coefficient of expansion (20°C~300°C)	10 <sup>-7</sup> K <sup>-1</sup>	91.5	+/-1.5
3	Softening point	°C	690	+/-10
4	SiO <sub>2</sub>	Wt.%	67.5	+/-0.5
5	Al <sub>2</sub> O <sub>3</sub>	Wt.%	3.5	+/-0.4
6	Na <sub>2</sub> O+K <sub>2</sub> O	Wt.%	14	+/-0.5
7	BaO+SrO	Wt.%	12.5	+/-1
8	Others	Wt.%	2.5	+/-0.5
9				