

# 济南泓海特种玻璃有限公司

## Jinan Honhai Glass Co., Ltd

### 玻璃管理化性能及主要化学组成

#### Lead glass tube property and composition

No.			Lead glass tube (Composition)	Tolerance
1	Density	g/cm <sup>3</sup>	2.85	+/-0.02
2	Coefficient of expansion (20°C ~ 300°C)	10 <sup>-7</sup> K <sup>-1</sup>	91	+/-1.5
3	Softening point	°C	635	+/-10
4	SiO <sub>2</sub>	Wt. %	62.5	+/-0.5
5	Al <sub>2</sub> O <sub>3</sub>	Wt. %	1.5	+/-0.4
6	Na <sub>2</sub> O+K <sub>2</sub> O	Wt. %	14	+/-0.5
7	PbO	Wt. %	20	+/-1.0
8	BaO+SrO	Wt. %		+/-1.0
9	B <sub>2</sub> O <sub>3</sub>	Wt. %		+/-0.5
10	Others	Wt. %	2	+/-0.5